

# Determination of formaldehyde emission according to the flask method

<b>Method</b>	EN 717-3 (March 1996) (SOP-KEMI-049)
<b>Flask material</b>	Polypropylene (lid of polyethylene)
<b>Flask volume</b>	500 ml
<b>Sample size</b>	25 x 25 mm, total 20 g (normally 4-5 pieces)
<b>Edge sealing</b>	No
<b>Conditioning</b>	optional
<b>Test duration</b>	3 hours
<b>Temperature</b>	40°C
<b>Humidity</b>	100 % (50 ml of water is added to the flask)
<b>Air exchanges</b>	Static measurement
<b>Results in</b>	Average of two samples in mg/kg dry sample (Report FJ)

